



TECHNICAL DATA SPECIFICATION

ANGLOKYD SS-4170-X

DESCRIPTION & APPLICATIONS

ANGLOKYD SS-4170-X is a short oil non-drying alkyd resin, with very good surface hardness and high gloss. It has also very good chemical and water resistance and flexibility.

ANGLOKYD SS-4170-X is suitable for stoving enamels in combination with melamine or urea resins at stoving temperatures of 130-140°C. ANGLOKYD SS-4170-X is also suitable for acid curing lacquers, NC Laquers and 2K PU varnish.

COMPOSITION

Type of oil:	Soya
Type of Polyol:	Penta. / Glycerine.
Oil length:	43% ±1
Non volatile:	70%± 1
Solvent:	Xylene

TECHNICAL CHARACTERISTICS

Viscosity Gardner:	Y-Z at 60%
Colour (Gardner):	> 8
Acid Value:	Max. 12

STORAGE

Resin should be stored indoors in the original containers in a dry place at 5-30° C

STABILITY

Provided above storage conditions are met, stability shall be maintained for 12 month.