



TECHNICAL DATA SPECIFICATION

ANGLOMIN 3400-IB

DESCRIPTION

ANGLOMIN 3400-60 resin is medium reactive, iso-butylated melamine formaldehyde resin designed as a general purpose, cross-linking agent for high quality stoving enamel finishes for metal.

APPLICATION

- High quality stoving enamels for appliances, cabinets, shelving etc.
- High quality stoving enamels for drums.
- Baking enamels for exterior metal surfaces.

SPECIFICATION

% Solids: 60%

Viscosity: X-Y

Acid Value: 1.0-2.0 max

Colour: 1.0 max

Solvent: Isobutanol

FEATURES

- Excellent Hardness
- Excellent chemical resistance
- High initial gloss and excellent gloss retention

STOVING CONDOITIONS

Depending on the use, the stoving conditions vary between 15 and 30 minutes at 170 - 210 °C.

STORAGE

Resin should be stored indoors in the original containers in a dry place at 5-30° C

STABILITY

Provided above storage conditions are met, stability shall be maintained for 6 month.