


## Colorama INSUTHERM - WB Heat Loss Curves

To whom it may concern,

Here below the curves show the loss of temperatures of to samples one of them is blank as a reference and the other is thermally insulated by our new brand INSUTHERM - WB (Heat Insulation Paint).


### 1- Blank Sample

Time (min.)	0	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
Temperature (°C)	154	134	117	104	90	90	78	70	64	59	55	51	47	44	41	39



### 2- Insulated Sample with Colorama INSUTHERM - WB

Time (min.)	0	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
Temperature (°C)	154	144	134	128	125	123	121	117	114	107	104	101	98	95	92	90



From the above tables and curves it's clear that the insulated sample lost temperature from 154°C to 90°C in 150 min. while the blank sample lost the same in 40 min. only which approves the high quality and excellent insulation capability of our brand INSUTHERM – WB.

UNITED COLORAMA  
يوناييتد كولوراما  
ملف ضريبي: ٠٠ / ٢٥١ / ١٦ / ٥١ - الإستمارة  
تم تسجيله في وزارة الاقتصاد

Regards

Colorama Coatings



Office : 7, Port Said St., ElShatby - Alexandria - Egypt  
Factory : Street 2C-2<sup>nd</sup> Industrial Zone - Borg El Arab City - Egypt  
Tel. & Fax +2 03 4595978 - 4591259 - 4593730

الإدارة : ٧ شارع بورسعيد الشاطبي - إسكندرية - مصر  
المصنع : مدينة برج العرب المنطقة الصناعية الثانية (شرق) مدخل ٢ ج  
تليفاكس : ٤٥٩٥٩٧٨ - ٤٥٩١٢٥٩ - ٤٥٩٣٧٣٠ +٢٠٣