

2873 CLEAR IN FC IMPREX

Product:

Impregnating wood decorative and protecting for external use.

Introduction:

It is a filler for decoration and for the wood protection both exterior and interior. It prevents the damage caused by insects, mushrooms, mould. It resists to bad weather, it does not crack. It penetrates deeply into wood so that it protects it from mould, woodworms and other insects. The product can be stained using the pastes PASIMP (BASE COLOURS red – orange – yellow – black – green – walnut – medium walnut – dark walnut) from 4% to 6%.

Kind of use:

Windows, matchboarding, attics, balconies, shutters, fences, furniture.

Support type :

Pine, spruce, ecc.

Characteristics :

1. Viscosity Ford 4 20°C
2. Viscosity Ford 4 20°C after catalysis
3. Solid content A
4. Solid content B
5. Solid content A+B
6. Pot-life (Life in pot 100 gr/20°C)
7. Practical useful life at 20°C
8. Dust free at 20°C after
9. Touch dry at 20°C after
10. Dry in deepness at 20°C after
11. Forced drying 40-45°C after
12. Light stability

- 12" +/- 1"
- /
- 10% +/- 1%
- /
- /
- unlimited
- /
- 30'
- 2h – 3h
- 6h
- /
- Good

Flash-point :

Please revert to the SDS

Specific weight:

A = 0,810

B =

Application :

By deeping, flow coating, brush, or spray.

Using method :

2873 Imprex in FC

94 – 96

Parts in LT/KG

Pigmented paste

4 – 6

Parts in LT/KG

110 Turpentine

5 – 10

On part A

Quantity to be applied :

- 1 or 2 coats it depends on your need (50/70 gr/sqm)

Sanding :

- After 16 – 24 hours (better the brushing than the sanding)

Overcoating :

- 8 – 12 hours by sealers or top coat with intermediate sanding

Storage :

At 20°C months (in the original sealed packing) part A

At 20°C months (in the original sealed packing) part B

General notes :

Always mix the products before use