

Colorama NC1007 MONOTOP

MONOTOP is high quality nitro-cellulose based enamel with excellent hardness and elasticity. The high quality of this product makes it suitable for the application as a glossy topcoat for almost any wood and steel works.

Properties and Areas of Use

- Tough, hard wearing flexible film, with excellent hardness, color retention and weathering resistance
- Good chemical resistance, and excellent water resistance
- Cures at low temperatures

Technical Coating Data @ 25 °C for mixed material

Finish	High Gloss
Color Range	As per shade card
Solids Volume	42 ± 2%
Dry Film Thickness Range	15-100 µm
Theoretical Spreading Rate	16.8 m ² /L @ 25 microns DFT (loss factors will apply in practice)
Surface Dry	15-20 min.
Recoat Interval	4 hours minimum 10 days maximum
Complete Cure	24 hours
Pot Life	Single Pack
Flash Point	28°C
Shelf Life	12 months (stored in a cool dry place)
Mixing Ratio by Weight	Single Pack
VOC	518 g/L ± 2%

Film Thickness and Spreading Rate:

	Minimum	Maximum	Typical
Film thickness, dry (µm)	15	100	25
Film Thickness, wet (µm)	38	238	60
Theoretical Spreading Rate (m ² /L)	28	4.2	16.8

Suitable Surfaces

- Steel and non-ferrous metals properly cleaned and primed with suitable anticorrosive primer.
- Wood must be abraded with sand paper No. 320 and primed with Colorama MONOFOND.
- All surfaces must be clean, dry & free from dust, dirt, grease, oil & rust.

Application Conditions

Substrate temperature should be 10°C or above for application and during cure and a minimum of 3°C above the dew point. Adequate dry air ventilation is recommended for optimum drying.

Application Information

Thinning should only take place after the two components have been thoroughly mixed.

Brush and Roller

Thin if required with 0-5% Paint Thinner Colorama NC.

Conventional Air Spraying

- Thin with 5-25% Paint Thinner Colorama NC, as required.
- Tip size - 2.0 mm
- Tip pressure - 60 psi (0.4Mpa) approximately

Airless Spraying

- Thin with 0-20% Paint Thinner Colorama NC, as required
- Tip size - 0.58-.79 mm approximately
- Tip pressure - 2100 psi (15Mpa) approximately

Cleaning Thinner

Equipment should be cleaned immediately after use with Paint Thinner Colorama NC.

Drying time:

Drying times are affected by air ventilation, temperature, film thickness and number of coats.

Substrate Temp.	10° C	25° C	40° C
Surface Dry	30 h	15 min.	10 min.
Through Dry	2 h	45 min.	30 min.
Dry to recoat, minimum	8 h	4 h	2 h

The given data serve as guideline only. The actual drying time differs according to film thickness, ventilation, humidity and underlying paint system.

Typical paint system:

Steel	Wood
<ul style="list-style-type: none">• PRIMALKYD Fast 1 x 50 µ• MONOTOP 1 x 25 µ	<ul style="list-style-type: none">• MONOFOND 2 x 50 µ• MONOTOP 1 x 25 µ

Storage:

Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling:

Handle with care. Stir well before use.

Packing Size:

5 L, 18 L and 200 Kg

Summary Safety Information

- Avoid inhalation of spray mist and skin contact by the use of masks, gloves and other personal protection. Eyes should be cautiously washed with water or proprietary wash, and medical attention obtained. Skin should be thoroughly washed using a cleanser and soap and water.
 - Product is flammable
 - No sparks or flames
 - No smoking

The information given in this data sheet represents test results & practical experience obtained under controlled conditions, and are correct to the best of our knowledge. However, as products are often used under different conditions, we can only guarantee the quality of our product, and reserve the right to change data without further notice.