

نتائج تحاليل لعينة مطبقة من مادة

PE 1002 RM - Primapox- RM

طبقا لمواصفة شركة بتروجت (PTJ – Spec. Int. -001)

& API 5L2 4th Edition

No.	Test	Standard	Results	Decision
1.	WFT	ASTM D1186	150 μ	O.K.
2.	Dry Film Thickness, DFT	“ “	95 μ	O.K.
3.	Solid content , by vol.	ASTM D 1644	64 %	O.K.
4.	Touch Dry	ASTM D 1640	2 hrs.	O.K.
5.	Dry to recoat	ASTM D 3029	10 hrs.	O.K.
6.	Impact,	ASTM D 3029	15 Joules	O.K.
7.	Bending	ASTM D 522	Pass	O.K.
8.	Adhesion	ASTM D 3359	Pass	O.K.
9.	Hardness	ASTM D 3363	10 N	O.K.
10.	Chemical Resistance Acetic Acid 2% one week Hot Water, (98±2)/24 hrs. Organic Solvents 2 weeks	ES. 190/2008	Pass Pass Pass	O.K. O.K. O.K.

SPC Director

Dr. Maher, A. El-Sockary



