

Colorama PE1002HBMD**PRIMABUILD - MD**

A two pack polyamide cured epoxy based, high build primer designed as a system primer for various paint systems. It can also be used as finish paint for structural steel and anti-chemicals flooring.

Properties and Areas of Use

- Tough hard wearing film
- Good chemical resistance
- Excellent water resistance
- Used with low slip additive for floors and decks

Technical Coating Data @ 25 °C for mixed material

Finish	Egg-shell
Color Range	Grey, White or Red
Solids Volume	73 ± 2%
Dry Film Thickness Range	100-500 µm
Theoretical Spreading Rate	4.87 m ² / L @ 150 microns DFT (loss factors will apply in practice)
Surface Dry	2 hours
Recoat Interval	8 hours minimum 7 days maximum
Complete Cure	7 days
Pot Life	4 hours
Flash Point	27°C
Shelf Life	24 months (stored in a cool dry place)
Mixing Ratio by Weight	10 Base component 1 Activator Component
VOC	251 g/L

Film Thickness and Spreading Rate:

	Minimum	Maximum	Typical
Film thickness, dry (µm)	100	500	150
Film Thickness, wet(µm)	137	685	206
Theoretical Spreading Rate (m ² /L)	7.3	1.45	4.87

Suitable Surfaces

- Steel and non ferrous metals properly prepared and blast cleaned to ISO-Sa2½
- Concrete free of contamination, dust and efflorescence, and properly prepared

Bare Steel:

Cleanliness: Blast – cleaning to Sa2 1/2 (ISO-8501-1:2007). Power tool cleaning to min. St2 (ISO 8501-1:2007) may be acceptable, subject to exposure conditions.

Shopprimed Steel:

Clean, dry and undamaged approved shopprimer

Coated Surfaces:

Clean, dry and undamaged compatible primer .

Other Surfaces:

For aluminium substrates , thorough washing and sweeping with a nonmetallic blast medium is required.

Application Conditions

Substrate temperature should be 10°C or above for application and during cure and a minimum of 3°C above the dew point. Adequate dry air ventilation is recommended for optimum drying.

Application Information

Thinning should only take place after the two components have been thoroughly mixed.

Brush and Roller

Thin if required with 0-5% Paint Thinner Colorama TH907EP.

Conventional Air Spraying

- Thin with 5-25% Paint Thinner Colorama TH907EP, as required.
- Tip size - 2.0 mm
- Tip pressure - 60 psi (0.4Mpa) approximately

Airless Spraying

- Thin with 0-20% Paint Thinner Colorama TH907EP, as required
- Tip size - 0.58-.79 mm approximately
- Tip pressure - 2100 psi (15Mpa) approximately

Cleaning Thinner

Equipment should be cleaned immediately after use with Paint Thinner Colorama TH907EP.

Drying time:

Drying times are affected by air ventilation, temperature, film thickness and number of coats.

Substrate Temp.	10° C	25° C	40° C
Surface Dry	8	4	2
Through Dry	16	8	6
Dry to recoat, minimum	24	12	8

The given data serve as guideline only. The actual drying time differs according to film thickness, ventilation, humidity and underlying paint system.

Typical paint system:

PRIMAPOX – GYM	1 x 50 µ
PRIMABUILD - MD	1 x 150 µ
URELUX	1 x 50 µ

Storage:

Keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling:

Handle with care. Stir well before use.

Packing Size:

5 L & 18 L

Summary Safety Information

- Avoid inhalation of spray mist and skin contact by the use of masks, gloves and other personal protection. Eyes should be cautiously washed with water or proprietary wash, and medical attention obtained. Skin should be thoroughly washed using a cleanser and soap and water.
- Product is flammable
- No sparks or flames
- No smoking

The information given in this data sheet represents test results & practical experience obtained under controlled conditions, and are correct to the best of our knowledge. However, as products are often used under different conditions, we can only guarantee the quality of our product, and reserve the right to change data without further notice.